



CHEMICAL & STAIN RESISTANCE DATA REPORT

QUICK SHIP LVT 2.5MM

5 MINUTE RATINGS	24 HOUR RATINGS
------------------	-----------------

STAINING AGENT	SURFACE DULLING	SURFACE ATTACK	COLOR CHANGE	SURFACE DULLING	SURFACE ATTACK	COLOR CHANGE
5% Acetic Acid	0	0	0	0	0	0
70% Isopropyl Alcohol	0	0	0	0	0	0
Mineral Oil	0	0	0	0	0	0
5% Sodium Hydroxide	0	0	0	0	0	0
5% Hydrochloric Acid	0	0	0	0	0	0
5% Ammonia	0	0	0	0	0	0
Bleach	0	0	0	0	0	0
5% Phenol	1	0	0	1	0	0
Gasoline	0	0	0	0	0	0
Sulfuric Acid	0	0	0	0	0	0
Kerosene	0	0	0	0	0	0
Olive Oil	0	0	0	0	0	0

RATING KEY
0 - No change (----)
1 - Slight change
2 - Moderate change
3 - Severe change

WWW.QUICKSHIPLVT.COM
 702-600-8043
SALES@QUICKSHIPLVT.COM